

XTRABOND™ 9500

MODIFIED POLYURETHANE SEALANT

XtraBond™ 9500 is a high performance, one component, permanently flexible, easy to use, multi-purpose fast cure modified polyurethane sealant. Xtrabond™ 9500 cures rapidly when exposed to atmospheric moisture to form a durable bond.

Features

- AAMA Certified
- Non-Yellowing
- Environmentally friendly
- No Solvents, Very Low VOCs
- Can Be Painted in 2 hours
- Fast Cure at a wide range of temperatures
- Aggressive Adhesion to common construction substrates
- Compatible with SBS Flashing

Applications

- Perimeter sealing of windows, doors & skylights
- Siding
- Construction Flashing Applications
- Sealing WaterProof Membrane
- Industrial Applications



Specifications

Skin Time	Less than 20 minutes @ 77° F/ 50% RH
Tack Free Time	Less than 1 hour @ 77° F/ 50% RH
Cure Rate	1/4" Bead per 24 Hrs
VOC	9 g/L (0.0751 lb/gal)
Elongation @ Break	450%
Shore A	35 +/- 5
Movement Capability %	25 %
UV Rating	No discoloration or change in appearance after 2500 hours of UV
Lap Shear	325 psi
Tensile Strength	250 psi
Straining	None
Low Temp Flexibility	Retained to -90 degrees
High Temp Flexibility	Up to 425° F for short periods
Sag	None



XTRABOND™ 9500

MODIFIED POLYURETHANE SEALANT

COLOR BROCHURE

COГOP BPOЧHOBE



SUPERIOR CAULKING & SEALANTS



ADDRESS:
23040 N 11TH AVE. STE 112
PHOENIX, AZ 85027

PHONE/FAX:
PH: 623-780-3160
FX: 623-478-2566

WEB:
INFO@PREMIERINDUSTRIAL.NET
WWW.PREMIERINDUSTRIAL.NET

www.xtrabond.com

www.xtrabond.com

www.xtrabond.com

www.xtrabond.com



